CE Marking Page 1 of 2	Cerámica Acústica S.L. 🙆				
Description of the product	LI2 705				
	 HISPAPLANO 9 UNE-EN 771-1 Mega brick of baked clay . Category I, piece LD (used for building masonry walls), double hollow brick. Piece with matching grooves in both edges. 				
Frequent uses	 Includes special matching tongues for plumbing and electrical installations. High level of flatness and cutting accuracy. Interior partitioning. Cavity walls and cladding. Partitioning of houses 				
Advantages	 Security for the technical direction, guaranteed by: Important quality certificates. A large number of tests carried out by approved bodies by ENAC, justifying the CTE requirements. It differs from other partitioning systems: Conduits for installations Very resistant partitioning Perfect finishes Reduction of debris An efficient application of the finish coating is achieved thanks to the great flatness and suitable absorption. 				
Presentation of the product	 Pallets are completely protected and packed with plastic. Presentation of pallet: Products Weight/unit Units/pallet Kg/m² Kg/pallet m²/pallet 				
	HispaPlano 20,50 24 56 492 8,8 Fitting 7 84 71 588 8,3				

Cerámica Acústica S.L.



CE Marking Page 2 of 2

TECHNICAL CHARACTERISTICS	HISPAPLANO 9 According to rule UNE-EN 771-1, annex ZA			
	Length		705 (T1,R1)	
Dimensions, Dimensional Tolerance and Range Class	Height		517 (T1,R1)	
	Width		90 (T1,R1)	
Flatness	≤ 4 mm		4 mm	
Plane parallelism	NPD			
Compressive Strength:	Average va	alue: 2 (N/mm²)	tested normal to the bed face of the unit)	
Dimensional Stability According to test (UNE EN 772-19)	Expansion because of moisture		0,5 mm/m	
Bond Strength: According to tabulated values given EN998-2	0,15 (N/mm²)			
Active Soluble Salts: According to test (EN 772-5)		NPD (S0)		
Reaction to Fire: Content of organic matter ≤1%	Class A1			
Water Absorption (According to annex C EN 771-1)	≤ 10 %			
Water Vapour Permeability: Tabulated values given in EN 1745	5/10			
	Apparent Density		625 (kg/m³) (D1)	
	Absolute Density		2010 (kg/m³) (D1)	
Direct Airborne Sound Insulation	% hollows		≤ 70%	
	Geometry and Shape (EN 772-16 y EN772-3)		See above	
Equivalent Thermal Conductivity: a) Calculation from finite elements	0,246 (W/m ºK)			
Durability Against Freeze Thaw	NPD			
Dangerous substances	NPD			
Certificates / rules	 Notified body number:0099 CPF certificate number: 0099-CPD-A73/0046 Awarding year for CE marking: 2006 Application rule: UNE-EN-771-1 (ANEXO ZA) 			
Edition date of the file:	12/12/08			
Cancel files on the date:	19/06/08			

 CERÁMICA ACÚSTICA SL, located in Ctra Corrales-Peleas de Abajo s/n (49700 Corrales del Vino Zamora), declares that the mega brick made from clay
 HISPAPLANO 9 and FITTING PIECE 9 manufactured in the factory above indicated, according to the annex ZA of the rule EN 771-1.
 Also, the evaluation system for conformity testing that has been chosen is 2+, evaluated by AENOR as notified body.

Date and Sign: 12/12/08 Fernando Riesco Prieto (administrator)